AIRTECH ADVANCED MATERIALS UK
The Causeway
Broadway Business Park
Chadderton, Oldham
Phone: +44 161 947 1610 E-mail: sales@airtech-amg.co.uk
Website: www.airtech-amg.co.uk

Data Sheet

WRIGHTLON® 3700

Low cost release film for commercial and wind energy applications

DESCRIPTION

Wrightlon® 3700 is a release film that is designed for low cost applications. Wrightlon® 3700 will release from epoxy, polyester and vinyl ester resin systems.

BENEFITS

- Good value for low to medium temperature applications.
- Blue colour is visible on laminate surface.
- Available in P16 perforation style, especially for infusion applications.

TECHNICAL DATA

		Test method
Material type	Polyolefin	
Elongation at break	500 %	ASTM D882
Tensile strength	30 MPa (4350 psi)	ASTM D882
Maximum use temperature	121°C (250°F)	
Materials to avoid	Phenolic resins/Strong oxidizers	
Colour	Blue	
Storage	Recommended storage temperature is 5°C to 40°C (41°F to 104°F). Store indoors in original packaging, do not stack rolls on end.	

SIZES

Thickness	Width	Forms Available*
25 µm (0.001 inch)	up to 2 m (80 inches)	SHT
33 µm (0.0013 inch)	up to 2 m (80 inches)	SHT
50 µm (0.002 inch)	up to 2 m (80 inches)	SHT

- For more sizes, see the *Commonly Used Sizes* chart in this section.
- Custom shapes and sizes are available, please contact Airtech for more information.

* SHT = sheeting

SUSTAINABILITY





NOTES

- The maximum use temperature is dependent upon the duration at maximum temperature and is process specific, Airtech recommends testing prior to use.
- Watch a demo video of Wrightlon® 3700 in the "Media Centre" on our website.

Last updated : 2025-02-06
Catalog position : Release films

As the conditions or methods of use, including storage, are beyond our control, Airtech UK, does not assume responsibility for the performance of this material for any particular use. The material is sold "as is". Airtech UK disclaims, and buyer waives, any and all implied warranties, including without limitation the implied warranties of merchantability and of fitness for particular use. The information contained herein represents typical properties and should not be used for specification purposes. Any translation is provided for your convenience only. The official language is English and the official law is England, United Kingdom.